(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(43) International publication date 24 December 2003 (24.12.2003)

PCT

(10) International publication number

WO 03/106759 A1

(51) International patent classification⁷: D06M 15/643, C09D 183/04, C08J 3/03

D06N 3/12,

(74) Representatives: CABINET PLASSERAUD etc., 84 rue d'Amsterdam, F-75440 PARIS CEDEX 09 (FR).

(21) International application number:

PCT/FR03/50012

(22) International filing date:

17 June 2003 (17.06.2003)

(25) Language of filing:

French

(26) Language of publication:

French

(30) Data relating to the priority:

02/07,491 18 June 2002 (18.06.2002)

FR

- (71) Applicant (for all designated States except US): TISSAGE ET ENDUCTION SERGE FERRARI SA [FR/FR]; Zone industrielle de la Tour du Pin, F-38110 SAINT-JEAN DE SOUDAIN (FR).
- (72) Inventors; and
- (75) Inventors, and (75) Inventors, Applicants (US only): MARTIN, Géraldine [FR/FR]; Saint Roch 1, F-38110 LA TOUR DU PIN (FR). PERILLON, Jean-Luc [FR/FR]; 22 chemin des Fayettes, F-26130 SAINT-PAUL TROIS CHATEAUX (FR).

- (81) Designated states (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HILLID, ILLIN, IS, IP, KE
- GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

 (84) Designated states (regional): ARIPO Patent (GH, GM,
- (84) Designated states (regional): ARIPO Patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European Patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[continued on next page]

As printed

- (54) Title: METHOD FOR COATING AN ARCHITECTURAL TEXTILE WITH AT LEAST ONE LAYER OF A SILICONE ELASTOMER USING AN AQUEOUS SILICONE EMULSION AND AN ARCHITECTURAL TEXTILE WITH SUCH A COATING
- (54) Titre: PROCEDE DE REVETEMENT D'UN TEXTILE ARCHITECTURAL AVEC AU MOINS UNE COUCHE D'ELAS-TOMERE SILICONE, À PARTIR D'UNE EMULSION SILICONE AQUEUSE ET TEXTILE ARCHITECTURAL AINSI RE-VETU
- (57) Abstract: The invention relates to the production of silicone membranes for architectural use, by means of coating an architectural textile with a silicone, in particular, but not exclusively on a glass fabric. The aim of the invention is a method in which the deposition on the architectural textile may be easily and rapidly achieved with a coating rate of less than 40 g/m². Said aim is achieved whereby said method comprises the following steps: deposition on said architectural textile of at least one layer of an emulsion of polyorganosiloxane (POS), which may be cross-linked to give an elastomer by polyaddition and comprising: (A) a POS with =SiVinyl groups, (B) a POS with =SiH groups. (C) a special adherence promoter (polyvinyl alcohol) or POS(OH), (D) a catalyst, (E) at least one surface active agent, (F) optionally a POS resin with =SiVinyl groups, (G) optionally a cross-linking inhibitor, (H) optionally a pH stabilising agent,(I) optionally a formulation additive. (J) optionally a charge and (K) water, with the condition that 0.05 <u></u> (C) <u><</u> 4 % by weight of the silicone phase, followed by cross-linking such that the weight proportion of the coating as a proportion of the dry weight of the architectural textile is less than 0.2 and preferably between 0.05 and 0.11.

(57) Abrégé: L'invention concerne la réalisation de membranes silicone architecturales obtenues à partir d'un revêtement par un silicone d'un textile architectural, en particulier mais non limitativement d'un tissu de verre. Le but est de fournir un procédé dans lequel le dépôt sur le textile architectural peut être aisément effectué à grande vitesse avec un taux de dépôt limité inférieur à 40 g/m². Pour atteindre ce but, le procédé comprend les étapes suivantes : dépôt sur ledit textile architectural ; d'nu moins une couche d'une émulsion aqueuse de polyorganosiloxane (POS) réticulable en élastonère par polyaddition et comprenant: (A) un POS à motifs ≡SiVinyle. (B) un POS à motifs ≡SiVinyle. (B) un POS à motifs ≡SiVinyle. (C) un promoteur d'adhérence spécial (alecol polyvinylique) ou POS (OH). (D) un catalyseur. (H) au moins un tensioactif. (F) éventuellement une résine POS à motifs ≡SiVinyle. (G) éventuellement un inhibiteur de réticulation. (H) éventuellement un agent de fixation du pH.(I) éventuellement un additif de formulation. (J) éventuellement une charge. (K) et de l'eau, avec la condition selon laquelle 0,05 ≤ (C)≤ 4 % en poids par rapport à la phase silicone, puis réticulation, de telle sorte que le rapport du poids de l'enduction exprimée en sec au poids du textile architectural soit inférieur à 0,2 et de préférence compris entre 0,05 et 0,11.

_